

L Number	Hits	Search Text	DB	Time stamp
-	8	313/623-625	USPAT	2004/06/23 16:15
-	912	313/623-625.ccls.	USPAT; EPO; JPO; DERWENT; IBM_TDB	2004/06/23 16:17
-	1	discharge and (cermet ceramic) and metal and sinter\$4 and (porous pore porosity) same (cermet ceramic) and crystal	USPAT; EPO; JPO; DERWENT; IBM_TDB	2004/06/23 16:18
-	3	discharge and (cermet ceramic) and metal and sinter\$4 and (porous pore porosity) same (cermet ceramic) and crystal\$	USPAT; EPO; JPO; DERWENT; IBM_TDB	2004/06/23 16:18
-	7	discharge and (cermet ceramic) and metal and sinter\$4 and (porous pore porosity) and crystal\$6	USPAT; EPO; JPO; DERWENT; IBM_TDB	2004/06/23 16:19
-	1309	discharge and (cermet ceramic) and metal and sinter\$4 and (porous pore porosity) and crystal\$6	USPAT; EPO; JPO; DERWENT; IBM_TDB	2004/06/23 16:22
-	1750	discharge and (cermet ceramic) and metal and sinter\$4 and (porous hole pore porosity) and crystal\$6	USPAT; EPO; JPO; DERWENT; IBM_TDB	2004/06/23 16:20
-	20	(discharge and (cermet ceramic) and metal and sinter\$4 and (porous hole pore porosity) and crystal\$6) and 313/623-625.ccls.	USPAT; EPO; JPO; DERWENT; IBM_TDB	2004/06/23 16:21
-	1221	445/22,23,26.ccls.	USPAT; EPO; JPO; DERWENT; IBM_TDB	2004/06/23 16:22
-	831	discharge and (cermet ceramic) and metal and sinter\$4 and (porous hole pore porosity) same (cermet ceramic) and crystal\$6	USPAT; EPO; JPO; DERWENT; IBM_TDB	2004/06/23 16:23
-	564	discharge and (cermet ceramic) and metal and sinter\$4 and (porous hole pore porosity) with (cermet ceramic) and crystal\$6	USPAT; EPO; JPO; DERWENT; IBM_TDB	2004/06/23 16:23
-	392	discharge and (cermet ceramic) and metal and sinter\$4 and (porous hole pore porosity) with (cermet ceramic) and crystal\$6 and phase	USPAT; EPO; JPO; DERWENT; IBM_TDB	2004/06/23 16:23